

Sikacrete® 211

One-component, cementitious,
pumpable and pourable concrete mix

Description	Sikacrete® 211 is a 1-component, portland-cement concrete containing factory blended coarse aggregate.
Where to Use	<ul style="list-style-type: none">■ Full depth repairs.■ On grade, above, and below grade on concrete.■ On horizontal, vertical and overhead surfaces.■ As a structural repair material for parking facilities, industrial plants, walkways, bridges, tunnels, dams and balconies.■ Filler for voids and cavities.
Advantages	<ul style="list-style-type: none">■ Pre-packaged coarse aggregate: Eliminates need to extend material in the field; Eliminates the risk of reactive aggregate.■ High bond strength.■ Compatible with coefficient of thermal expansion of concrete.■ Increased resistance to deicing salts.■ Simple-to-use labor-saving system.■ Easily mixed.■ Good freeze/thaw resistance.■ Easily applied to clean, sound substrate.■ Not a vapor barrier.■ Not flammable
Coverage	Approximately 0.65 ft. ³ /unit
Packaging	80 lb. multi-wall bag.

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life	1 year in original, unopened packaging.
Storage Conditions	Store dry at 40°-95°F (4°-35°C). Condition material to 65°-75°F before using.
Color	Concrete gray when mixed.
Mixing Ratio	Mix with clean potable water at rate of up to 1 gallon per bag. Start with 4/5 gallon and mix to consistency required with remainder of gallon.
Application Time	Initial Slump 5"-7"; Slump at 30 minutes >4"
Flexural Strength (ASTM C-78)	28 days 700 psi (5.0 MPa)
Splitting Tensile Strength (ASTM C-496)	28 days 750 psi (3.4 MPa)
Bond Strength* (ASTM C-882 modified)	28 days 1,500 psi (15.2 MPa)
Compressive Strength (ASTM C-39)	
1 day	2,000 psi (13.8 MPa)
7 days	4,500 psi (31.0 MPa)
28 days	5,000 psi (37.9 MPa)
Shrinkage (ASTM C-157)	28 days <0.05%
Chloride ion permeability (Astm C-1202)	28 days <1,500 Coloumbs

* Mortar scrubbed into substrate.

Construction



Sika®

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

How to Use	
Substrate	Concrete, mortar, and masonry products.
Surface Preparation	<p>Concrete: Remove all deteriorated concrete, dirt, oil, grease, and all bond-inhibiting materials from surface. Be sure repair area is not less than 1 in. in depth. Preparation work should be done by high pressure water blast, scabblor, or other appropriate mechanical means to obtain an exposed aggregate surface with a minimum surface profile of $\pm 1/8$ in. (CSP-7). Saturate surface with clean water. Substrate should be saturated surface dry (SSD) with no standing water during application.</p> <p>Reinforcing Steel: Steel reinforcement should be thoroughly prepared by mechanical cleaning to remove all traces of rust. Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water after mechanical cleaning. For priming of reinforcing steel use Sika® Armatex® 110 EpoCem (consult Technical Data Sheet).</p>
Priming	For priming of reinforcing steel use Sika® Armatex® 110 EpoCem (consult Technical Data Sheet).
Mixing	Place 4/5 of 1 gallon water in mixing container. Add Sikacrete® 211 while continuing to mix. Add additional water up to 1 gallon total. Mix to a uniform consistency, maximum 3 minutes. Mechanically mix with a low-speed drill (400-600 rpm) and paddle or in appropriate size mortar mixer or concrete mixer.
Application	Form and pour or pump applications: Pre-wet surface to SSD. Ensure good intimate contact with the substrate is achieved. To accomplish this, material should be scrubbed into the substrate or other suitable means should be employed such as vibration of the material or pumping under pressure. Vibrate form while pouring or pumping. Pump with a variable pressure pump. Continue pumping until a 3 to 5 psi increase in normal line pressure is evident then STOP pumping. Form should not deflect. Vent to be capped when steady flow is evident, and forms stripped when appropriate.
Tooling & finishing	As per ACI recommendations for portland cement concrete, curing is required. Moist cure with wet burlap and polyethylene, a fine mist of water or a water based* compatible curing compound. Curing compounds adversely affect the adhesion of following layers of mortar, leveling mortar or protective coatings. Moist curing should commence immediately after finishing. Protect newly applied material from direct sunlight, wind, rain and frost.
	*Pretesting of curing compound is recommended.
Limitations	<ul style="list-style-type: none"> ■ Application thickness: Minimum 1 in. (25 mm); Maximum 8 in. (200 mm) ■ Minimum ambient and surface temperatures 45°F (7°C) and rising at time of application. ■ Using SikaLatex®, SikaLatex® R or similar products will result in loss of slump and slump retention. Field tests for suitability are strongly recommended.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C.P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikacrete are registered trademarks. Printed in Canada.

